

**Description:** Because of its good UV-resistance, Wood Tar is ideal for above-ground structures such as sheds, poles, fencing etc. and can be applied to surfaces that have been painted with bitumen and carbolineum. Weather-resistant, quick-drying, moisture-regulating and easy to apply. For exterior use.

**Application**

Apply in thin coats using a brush, bent head brush or roller.

**Dilute with:** Ready to use, dilute with approximately 5% white spirit if required.

**Covers:** Heavily dependent on the coating thickness and the structure of the surface to be treated.

**Drying time at 23°C:** heavily dependent on the coating thickness applied. Dust dry after approximately 2 - 4 hours. Apply second coat after 5 - 6 hours.

## SYSTEM CONSTRUCTION

**Preparation**

The substrate must be dry and free from grease. Remove old poorly adhering layers on wood and sand using sandpaper.

## TECHNICAL DATA

**Dilute with:** Ready to use

**Hazard classification:** See safety information sheet (MSDS)

**Tool cleaning instructions:**

The use of disposable brushes is recommended.

**Storage:** Minimum of 12 months in the tightly sealed original packaging in a dry, cool and frost-free place.

**General information**

Do not use in temperatures below 10°C, in direct sunlight or when rain or fog is expected. Replace lid firmly after use and store in a cool and frost-free place.

Harmful particles may be released when sanding or scraping off coats of paint, etc. Work in a well-ventilated area and use the correct protective equipment if necessary.

**Warning:** Used rags and cloths can ignite if they become overheated. Always spread them out and leave outside to dry or pour water over them.

**Surplus product:** This paint and the packaging should be disposed of at a collection point for hazardous or special waste.