

Description: Glossy, transparent wood stain with UV filter based on alkyd resin. Provides 4 years of durable protection

Application: Suitable for external use such as wooden wall cladding, fascias, doors, window frames etc. The colour of the wood and of any existing clear wood protective layers will influence the colour of the end result. Finess Wood stain Transparent 'Colourless' can be used outside as a priming coat but it is less suitable as a final coat!

Properties:

- Higher coat thickness
- Less solvents
- Moisture-controlling
- Weather-resistant.
- Economical to apply
- Very easy to apply
- Glossy

Colours: Colourless and various wood colours.

Handling: Stir thoroughly prior to use. Apply with a flat brush in the direction of the grain. Dilute the first coat on unprimed wood with max 5 % white spirit to ensure better penetration is obtained. Do not dilute the following coats. Apply 3 coloured layers to unpainted wood. Always work wet-on-wet to avoid visible strokes. Sand lightly in the direction of the grain between coats and remove any dust.

Covers: Approx. 16-18 m²/litre per coat, depending on the surface.

Drying time at 23°C and relative humidity of 65%:
Dust-dry after approx. 4 hours.
Can be painted over after approx. 18 hours.

SYSTEM CONSTRUCTION

Substrate: The surface must be firm, clean, dry and free from dust or grease. Seal holes and chinks with a wood filler.

Unprimed wood: Degrease, lightly sand down in the direction of the grain, round off any sharp edges and repair open wood joints, sealed joints and such with a suitable product. After hardening, sand it all down and make it free from dust. Next, apply 3 colour coats.

Treated wood in poor condition: Remove all poorly adhering paint using paint stripper or a blowtorch/hot air paint removal gun. Then treat as "Unprimed wood".

Treated wood in good condition: Degrease with a degreasant and allow to dry. Next, lightly sand in the direction of the grain and apply 1 or 2 coloured coats.

TECHNICAL DATA

Binding agent:	Glycerophthalic resins and polymerised oil
Pigments:	Laminated fillers and transparent iron oxide
Solvent:	White spirit
Solid components:	55% by volume
SG:	Approx. 1 g/ml
Viscosity:	ICI Rotothinner 6-7 Poise @ +20°C
Recommended coat thickness:	35 microns dry
Degree of gloss:	Gloss. 70-85% with Gardner 60° gloss meter
Tint:	Transparent and various wood colours
Dilute with:	White spirit
Flash point:	39°C
Hazard classification:	See safety information sheet (MSDS)
Tool cleaning instructions:	White spirit or brush cleaner
Features:	Moisture-controlling. The wood grain will remain visible.

Storage: Minimum of 12 months in the tightly sealed original packaging in a dry, cool and frost-free place.

General: We recommend applying at temperatures between +8°C and +30°C. Do not apply in direct sunlight or when it is likely to rain. After use, close the container correctly, turn it around for a few seconds to ensure that skin formation cannot occur and store in an upright position.

Surplus product: This paint and the packaging should be disposed of at a collection point for hazardous or special waste.