

## Technical datasheet

# RADIATOR spray paint 400 ml

High gloss spray paint for radiators and central heating pipes. Heat resistant up to 80°C. Excellent for hard to paint surfaces such as radiators (not cast iron) and heating pipes. For interior use.

**Substrate:** The surface must be clean, dry and free of grease. Remove any rust and flaking paint layers first before sanding. Mask off the surrounding area. Apply a basecoat with SPRAYTONE Primer to untreated metal.

### Handling:

Before use, shake the aerosol can vigorously for at least 1 minute, during which time the mixing ball can be heard (also shake occasionally during use). Spray a sample first. Apply in 2 to 3 thin layers at a distance of approx. 20-30 cm. Apply the next layer within 30 minutes or after curing (6 hours). After use, reverse the spray can and spray the paint residues out of the valve. Application temperature: min. 15°C. Consumption: Approx. 1-2 m<sup>2</sup> per 400 ml.

**Drying time (at 23°C and relative humidity of 65%):** Recoat within 30 minutes or after 6 hours. The drying time depends on the ambient temperature, the relative humidity and the coating thickness.

### General:

- Turn off heating elements before painting and turn back on after 72 hours.
- It is better to apply several thin layers, instead of one thick layer.
- Work in a well ventilated area. If necessary, use appropriate safety equipment.
- Do not use at temperatures below 10°C., when it is likely to rain, frost is expected, or in direct sunlight.
- Store in a dry, cool and frost-free place.

### Technical data

<b>Content</b>	400 ml
<b>Colour</b>	White (RAL 9016), pure white (RAL 9010) and cream white (RAL 9001).
<b>Heat resistant</b>	Up to 80°C
<b>General</b>	The spray can must be kept at room temperature (minimum of 15°C). Never place the spray can on a heat source.
<b>Storage</b>	Minimum of 12 months in the tightly sealed original packaging in a dry, cool and frost-free place.
<b>Surplus product</b>	This paint and the packaging should be disposed of at a collection point for hazardous or special waste.
<b>Hazard classification</b>	See MSDS

The effectiveness of our systems is based on developments in the raw material suppliers' materials and our practical experience. We cannot, however, be held liable without qualification for the work produced based on those systems, as the final result will be determined, in part, by the state of the substrates and other factors that are outside of our control. The current publication makes previously published technical sheets null and void.