

**Description:** Water-based, colourless fixing agent based on synthetic resin for substrates with a powdery, porous or highly absorbent surface. Deep penetrative capacity, improves adhesion to the substrate and increases the efficiency of the finishing coat. Solvent-free, low-odour and quick drying. For interior and exterior use.

**Use:** As a primer on powdery and absorbent substrates. Suitable substrates are, for example: cement and plasterwork, concrete, brickwork, plasterboard, board, etc.

**Properties:**

- Stabilises powdery surfaces
- Good penetration performance
- Improves finishing coat adhesion
- Improves finishing coat coverage
- Solvent-free and virtually odourless
- Quick drying

**Colour:** Colourless.

**Handling:**

Shake and stir before use. Apply in 1 coat preferably using a square pasting brush or a woolly roller. Never allow this product to form a film.

**Covers:** Approx. 6-10 m<sup>2</sup>/litre per coat. The stated performance is theoretical. Actual consumption depends on the nature and the structure of the surface and the application method.

**Drying time at 23°C and relative humidity of 65%:**

Dust-dry after approximately 1 hour.

Can be painted over after approximately 4 hours.

Variations in coating thickness, temperature, relative humidity etc. affect the drying time.

### SYSTEM CONSTRUCTION

**General:**

The surface must have a load-bearing capacity and must be fully set, dry and free from dust or grease. Sand and repair surface irregularities. Remove and/or repair all loose and unstable coats. When using externally, remove all algae and moss.

**New, untreated substrates**

- Prime absorbent and highly absorbent surfaces in their entirety using SPS Stabilising primer (prevent glossy patches).
- Thoroughly clean powdery surfaces. Prime with SPS Stabilising primer after allowing to dry.

**Existing, non-load-bearing substrates**

- Thoroughly remove loose coats.
- Thoroughly wash powdery coats and allow to dry.
- Carry out any repairs.
- Prime with SPS Stabilising primer.

The aforementioned systems form a general description of the most common substrates. Please contact SPS bv for specific applications and/or detailed advice.

TECHNICAL DATA (apply to transparent/colourless)

<b>Binding agent:</b>	Styrene acrylic resin
<b>Solvent:</b>	Water
<b>Solid components:</b>	11% v/v
<b>Equivalent weight:</b>	Approximately 1.00 g/ml
<b>Recommended coat thickness:</b>	Do not allow this product to form a film.
<b>Dilute with:</b>	Do not dilute!
<b>Hazard classification:</b>	See MSDS
<b>Tool cleaning instructions:</b>	Use water and soap.

**Shelf life** Minimum of 12 months in the tightly sealed original packaging in a dry, cool and frost-free place.

**General:** Do not use at temperatures below +8°C. Only use when the surface temperature is at least 3°C above the dew point temperature. Do not apply outdoors when it is likely to rain or when frost is expected. Do not apply outdoors in direct sun. When using this product, always use the necessary personal protective equipment. Always ventilate in a suitable way during use.

**Surplus product:** This paint and the packaging should be disposed of at a collection point for hazardous or special waste.